

What is claimed is:

1 1. A grout composition that sets after being mixed with
2 water comprising:

3 an anhydrous structural filler that comprises between 10
4 and 90% by weight of the total grout composition; and
5 a moisture curable polymer.

1 2. The grout composition of claim 1 which further
2 comprises an effective amount of a retarding agent to provide
3 a retarding effect on the setting of the grout composition.

1 3. The grout composition of claim 1 wherein the
2 anhydrous filler comprises Portland cement.

1 4. The grout composition of claim 3 wherein the
2 Portland cement is rapid hardening Portland cement.

1 5. The grout composition of claim 1 wherein the
2 Portland cement comprises between 30 and 55% by weight of the
3 total grout composition.

1 6. The grout composition of claim 1 further comprising
2 a color.

1 7. The grout composition of claim 1 further comprising
2 a stabilizer.

1 8. The grout composition of claim 1 further comprising
2 a rheological agent.

1 9. The grout composition of claim 1 further comprising
2 a plasticizer.

1 20. The kit of claim 11 further comprising a
2 plasticizer.

Sub
A2
cont.

1 21. The kit of claim 11 wherein the moisture curable
2 polymer is selected from the group consisting of
3 polyacetoacetate, polyisocyanates and mixtures thereof.

1 22. A method of filling a gap or crevice comprising:
2 providing a moisture curable compound; and
3 adding to the moisture curable compound a structural
4 filler, wherein upon exposure to water, the moisture curable
5 filler forms a polymeric matrix along with the structural
6 filler to fill the gap or crevice.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100